

Penetration-Grade Bitumen

Pen 60/70 and 80/100 in drums, bulk and bitutainers — for roads and infrastructure on three continents.

Parameter	Specification
Grades	Pen 60/70, Pen 80/100
Penetration @ 25°C	60-70 / 80-100 dmm
Softening Point	49-56 °C / 45-52 °C
Flash Point (COC)	≥ 232 °C
Ductility @ 25°C	≥ 100 cm
Solubility in TCE	≥ 99.0 wt%
Packaging	Drums (180kg) · Bitutainer · Bulk